

épaisseur	EPS 30	XPS blau	XPS lila	XPS Plus lila		Klebit PET Eco50	PIR 33	SwissporPIR Premium	Kerdyn 115	PUR 500
	W/mk 0.033	W/mk 0.035-0.039	W/mk 0.034	W/mk 0.025-0.027		W/mk 0.032	W/mk 0.025-0.027	W/mk 0.02	W/mk 0.0332	W/mk 0.087
10 mm	2.11	2.16	2.19				1.80			3.46
15 mm	1.60						1.34			2.87
20 mm	1.29	1.32	1.35	1.03*	1.10	1.25	1.07	0.89	1.30	2.45
25 mm	1.08						0.88			2.14
30 mm	0.93	0.95	0.97	0.73*	0.78	0.90	0.76	0.63	0.93	1.90
35 mm	0.81									1.71
40 mm	0.72	0.74		0.57*	0.61	0.70	0.59	0.48	0.73	1.55
45 mm										1.42
50 mm	0.59	0.61		0.46*	0.50	0.58	0.48	0.39	0.60	1.31
55 mm										1.21
60 mm	0.50	0.52		0.39*	0.42	0.49	0.40	0.33	0.51	1.13
70 mm	0.44					0.42			0.44	1.00
80 mm	0.39	0.40		0.30*	0.32	0.37	0.31	0.25	0.39	0.89
90 mm						0.34			0.35	
100 mm	0.31	0.32				0.30	0.25	0.20	0.31	
120 mm	0.26	0.27				0.26		0.17	0.26	
140 mm	0.23	0.23		* pour laminage des deux faces, étanche aux gaz (sandwich)		0.22		0.15	0.23	
160 mm	0.20	0.21				0.19		0.13	0.20	
180 mm	0.18	0.18				0.17		0.11		
200 mm	0.16	0.17				0.16		0.10		