

Stärke	EPS 30	XPS blau	XPS lila	XPS Plus lila		Klebit PET Eco50	PIR 33	SwissporPIR Premium	Kerdyn 115	PUR 500	
	W/mk 0.033	W/mk 0.035-0.039	W/mk 0.034	W/mk 0.025-0.027		W/mk 0.035	W/mk 0.025-0.027	W/mk 0.02	W/mk 0.0332	W/mk 0.087	
10 mm	2.11	2.16	2.19				1.80			3.46	
15 mm	1.60						1.34			2.87	
20 mm	1.29	1.32	1.35	1.03*	1.10	1.35	1.07	0.89	1.30	2.45	
25 mm	1.08					1.13	0.88			2.14	
30 mm	0.93	0.95	0.97	0.73*	0.78	0.97	0.76	0.63	0.93	1.90	
35 mm	0.81									1.71	
40 mm	0.72	0.74		0.57*	0.61		0.59	0.48	0.73	1.55	
45 mm										1.42	
50 mm	0.59	0.61		0.46*	0.50	0.63	0.48	0.39	0.60	1.31	
55 mm										1.21	
60 mm	0.50	0.52		0.39*	0.42		0.40	0.33	0.51	1.13	
70 mm	0.44								0.44	1.00	
80 mm	0.39	0.40		0.30*	0.32		0.31	0.25	0.39	0.89	
90 mm									0.35		
100 mm	0.31	0.32				0.33	0.25	0.20	0.31		
120 mm	0.26	0.27						0.17	0.26		
140 mm	0.23	0.23		* bei beidseitiger gasdichter Kaschierung (Sandwich)				0.15	0.23		
160 mm	0.20	0.21							0.13	0.20	
180 mm	0.18	0.18							0.11		
200 mm	0.16	0.17					0.17		0.10		